




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61F	A2	(11) International Publication Number: WO 93/16656 (43) International Publication Date: 2 September 1993 (02.09.93)
<p>(21) International Application Number: PCT/US93/02008</p> <p>(22) International Filing Date: 18 February 1993 (18.02.93)</p> <p>(30) Priority data: 07/838,577 19 February 1992 (19.02.92) US</p> <p>(71) Applicant: JOINT MEDICAL PRODUCTS CORPORATION [US/US]; 860 Canal Street, Stamford, CT. 06902 (US).</p> <p>(72) Inventors: CONTA, Robert, L. ; 32 Shadow Lane, Wilton, CT 06897 (US). DECARLO, Alfred, F., Jr. ; 66 Denise Lane, Stamford, CT 06905 (US). NOILES, Douglas, G. ; 114 Elm Place, New Canaan, CT 06840 (US).</p>		<p>(74) Agent: KLEE, Maurice, M.; 1951 Burr Street, Fairfield, CT 06430 (US).</p> <p>(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>Without international search report and to be republished upon receipt of that report.</i></p>

(54) Title: SINTERED COATINGS FOR IMPLANTABLE PROSTHESES



(57) Abstract

A sintered coating (13) for an implantable prosthesis (10) is provided having 1) interstices into which tissue or bone can grow, and 2) increased surface roughness which provides enhanced initial press-fit fixation. In certain embodiments, the coating includes at least two sets of particles (46, 48) having different mean diameters. The sizes and numbers of particles are chosen so as to produce a matrix of smaller particles (48) in which are embedded a lesser number of spaced-apart larger particles (46). The smaller particles (48) provide support for the larger particles (46), and the larger particles (46) stand proud of the smaller particles (48) to provide the enhanced surface roughness. In other embodiments, the coating includes both generally smaller spherically-shaped (SS) particles and generally larger non-spherically-shaped (NSS) particles, with the NSS particles providing enhanced surface roughness and the SS particles providing support for the NSS particles.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

5

SINTERED COATINGS FOR IMPLANTABLE PROSTHESESBACKGROUND OF THE INVENTION1. Field of the Invention

10 This invention relates to implantable prostheses and in particular to an improved sintered coating for such prostheses.

2. Description of the Prior Art

15 For at least the past twenty years, implantable prostheses have been coated with metal particles so as to provide a surface into which bone or tissue can grow. Such coatings have been applied by plasma spray and/or sintering. See, for example, Hahn, U.S. Patent No. 3,605,123 and Pillier, U.S. Patent No. 4,206,516. As a general rule, plasma spray coatings have a
20 smaller void space than sintered coatings and thus are somewhat less preferred.

At present, a number of sintered coatings are in commercial use. The particles employed in these coatings are normally selected by sieving. They thus
25 have a single-mode distribution about a mean diameter value. Typically, the mean value has been in the range from about 0.006 inches (150 microns) to about 0.040 inches (1000 microns). The breadth of the distribution about the mean will depend upon the
30 sieves used to select the particles.

Sintered coatings of this type have been used in both single layer and multi-layer constructions. Also, they have been applied to prostheses having both smooth and stepped outer surfaces. See, for example,
35 Noiles, U.S. Patent No. 4,790,852.

One of the problems with the existing sintered coatings has been that relatively low levels of

surface friction exist at the interface between the coating and the bone. Most prostheses are implanted by press fitting into a prepared cavity in the patient's bone. A high level of friction at the coating-bone interface is thus desirable because it helps provide a more stable initial fixation of the prosthesis in the prepared cavity. An initial stable fixation of the prosthesis has been found to increase the likelihood of bone ingrowth.

SUMMARY OF THE INVENTION

In view of the foregoing state of the art, it is an object of this invention to provide improved sintered coatings for implantable prostheses. More particularly, it is an object of the invention to provide sintered coatings which provide a high degree of surface friction at the coating-bone interface. It is a further object of the invention to provide improved coatings which can be readily manufactured using conventional techniques.

To achieve the foregoing and other objects, the invention provides a sintered coating having an irregular surface produced by the use of particles having at least a bimodal size distribution, as opposed to the single-mode size distribution used in the prior art. As used herein, the term "at least a bimodal size distribution" means that a plot of number of particles versus particle diameter has at least two discernible peaks. Such plots can be readily constructed using sieving techniques to construct a histogram or by simply counting and measuring particles for a representative portion of a coated prosthesis. In this connection, the diameter of a particle is defined as the longest chord between any two points on the surface of the particle.

In certain embodiments of the invention, the particles making up the coating are all substantially spherically-shaped, that is, their cross-sections are

substantially circular. For ease of reference, such substantially spherically-shaped particles will be referred to herein and in the claims as simply "spherically-shaped particles" or as "SS particles."

5 In other embodiments, some of the particles are spherically-shaped while others have an irregular shape like that of grains of table salt. These particles are substantially aspherical, sometimes acicular, e.g., the particles may have cross-sections
10 which are rhombic in form. For ease of reference, the irregularly-shaped particles will be referred to herein and in the claims as "non-spherically-shaped particles" or as "NSS particles." The above definition of the diameter of a particle is applicable
15 to coatings containing only SS particles. When the coating contains both SS and NSS particles, the diameter of a particle is then defined as the diameter of the smallest hole through which the particle may pass.

20 In accordance with the invention, it has surprisingly been found that the use of smaller SS particles mixed with generally larger NSS particles provides a stronger sintered bond strength between the particles and the substrate than is obtained by the
25 use of smaller NSS particles mixed with larger NSS particles. That is, the use of SS particles is critical to the effectiveness of the invention.

When SS and NSS particles are used, at least one of the peaks of the at least bimodal size distribution
30 corresponds to SS particles while at least another of the peaks of the at least bimodal size distribution corresponds to NSS particles. For a size distribution having just two discernible peaks, i.e., a bimodal distribution, the smaller mean diameter preferably
35 corresponds to the SS particles and the larger mean diameter preferably corresponds to the NSS particles. For a size distribution having more than two

discernible peaks, i.e., a multimode distribution, there is preferably at least one peak corresponding to SS particles whose mean diameter is smaller than the smallest mean diameter of any of the peaks corresponding to the NSS particles, that is, there are preferably SS particles which are smaller than the NSS particles so that the SS particles can provide support for the NSS particles on the surface of the prosthesis.

10 The at least bimodal size distribution is preferably achieved by mixing together at least two sets of sieve-selected particles having different mean diameters. In general, it is preferred to select amounts of particles from the at least two sets so that the final distribution of particles includes more small particles than large particles. For example, for a coating made from two sets of sieve-selected particles, the ratio of the number of small particles to the number of large particles in the final distribution is preferably in the range from about 4:1 to about 40:1. When a combination of SS and NSS particles is used, the final distribution of particles can include approximately equal numbers of small and large particles. For example, the range of SS to NSS particles (SS:NSS) is preferably from about 1:1 to about 20:1.

20 When SS and NSS particles are used, the advantages of the invention can be achieved even though the mean diameters of the SS and NSS particles are approximately equal. Accordingly, for these embodiments, the size distribution of the particles making up the coating need not be at least bimodal as in the case when only SS particles are used.

30 The particle mixture of the invention is applied to a prosthesis using the conventional techniques employed with single-mode particle distributions. Accordingly, the invention can be readily put into

practice with essentially no changes to existing manufacturing techniques, which represents an important advantage of the invention.

5 In certain preferred embodiments, the particles are applied in substantially a single layer. In other preferred embodiments, the single layer is applied to a prosthesis having a stepped outer surface.

10 In practice, it has been found that prostheses coated with SS particles having size distributions of the type disclosed herein have significantly higher levels of surface friction in comparison to prostheses coated with similar particles having a single-mode distribution. The combination of SS and NSS particles has been found to produce even higher levels of surface friction.

15 The accompanying drawings, which are incorporated in and constitute part of the specification, illustrate the preferred embodiments of the invention, and together with the description, serve to explain the principles of the invention. It is to be understood, of course, that both the drawings and the description are explanatory only and are not restrictive of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

25 Figures 1A, 1B, and 1C are schematic diagrams illustrating typical constructions of prior art coatings.

30 Figures 2A, 2B, and 2C show particle size distributions for the constructions of Figures 1A, 1B, and 1C, respectively.

Figures 3A, 3B, and 3C are schematic diagrams illustrating representative constructions of coatings prepared in accordance with the invention.

35 Figure 4 is a plan view of the coatings of Figures 3B and 3C.

Although SS particles have been used for purposes of illustration in Figures 3 and 4, it is to be

understood that the diagrams also apply to combinations of SS and NSS particles. In such embodiments, the larger particles shown in the figures are preferably NSS particles and the smaller particles
5 are preferably SS particles.

Figure 5 shows the particle size distribution for the coatings of Figure 3. As discussed above, for embodiments employing SS and NSS particles, both the mean diameter values (d) and the particle number
10 values (n) for the two types of particles can be less disparate and in some embodiments either or both of these values can be substantially the same, i.e., n_{SS} can be approximately equal to n_{NSS} and/or d_{SS} can be approximately equal to d_{NSS} .

15 Figure 6 shows an acetabular cup employing a coating of the invention.

Figure 7 is an expanded view of a portion of the surface of the acetabular cup of Figure 6.

Figures 8 and 9 are photomicrographs showing a
20 coating prepared in accordance with the invention and having SS and NSS particles. The magnification in Figure 8 is 20X while that in Figure 9 is 40X.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

As described above, the present invention relates
25 to an improved sintered coating for implantable prostheses. The invention can be applied to all types of metal prostheses now known or subsequently developed, including, for example, hip and knee joint replacement prostheses. As an example, Figure 6 shows
30 an acetabular cup 10 having a body 12 and a coating 13 constructed in accordance with the invention.

The sintered metal coating is composed of a biocompatible metal, such as, pure titanium, a titanium alloy (e.g., Ti 6Al 4V; ASTM-F136), or a
35 cobalt-chromium alloy (ASTM-F75). Typically, the metal coating will have the same composition as that of the underlying prosthesis.

The coating is applied to the prosthesis using conventional sintering techniques known in the art. The sintering is performed in a high temperature, vacuum furnace. The particles are applied to the prosthesis in a binder which is volatilized during the sintering process. Various companies provide coating services for metal prostheses which can be used in the practice of the invention, including Bio-Vac Inc. (Southfield, Michigan), Hy-Vac Technologies, Inc. (Detroit, Michigan), and Astro Met, Inc. (Cincinnati, Ohio).

I. SS/SS Coatings

In accordance with certain embodiments of the invention, the surface of the coating is made irregular through the use of SS particles having at least a bimodal size distribution (referred to herein as an "at least bimodal SS/SS coating" or simply an "SS/SS coating"). Preferably, the bimodal size distribution is obtained by forming a mixture of at least two sets of sieve-selected particles having different mean diameters. The mixture is then used to coat the prosthesis.

The mean diameters for the at least two sets of particles and the numbers of particles from the sets are chosen so that 1) the final surface has spaced-apart larger particles embedded in a matrix of smaller particles, and 2) the larger particles stand proud of the smaller particles. The spaced-apart larger particles provide the desired roughness for the final surface. The smaller particles provide support for the larger particles so that the larger particles can resist the shear forces encountered during implantation and use of the prosthesis.

In contrast, if SS particles having a single-mode distribution were used to form a spaced-apart pattern having the same degree of roughness, the result would be a surface coating having many particles standing

alone and therefore having only one point of integration with the prosthesis. Such isolated particles would have low shear strength and would be unsuitable for implantation in the body. The provision of a matrix of smaller particles solves this problem by providing numerous points of integration for each of the particles, i.e., both the smaller and the larger particles. The result is a strong, integrated coating having high shear strength. Moreover, the combination of at least two sets of particles produces a surface having numerous voids into which bone or tissue can grow.

Although the invention can be practiced with more than two sets of particles, for most applications a two set system will be adequate. To achieve 1) spaced-apart larger particles in a matrix of smaller particles and 2) larger particles standing proud of smaller particles, the larger particles for a two set system will generally have a mean diameter in the range of from about 2 to about 7 times the mean diameter of the smaller particles. Also, the number of smaller particles will be generally between about 4 and about 40 times the number of larger particles.

Furthermore, to insure that the larger particles stand proud of the smaller particles, the coating thickness should at most be a few layers and preferably should approach a single layer. Along these same lines, a stepped surface is preferred since the steps provide additional points of integration for the particles and contribute to the overall irregularity (roughness) of the final surface.

In practice, a mixture of equal measured volumes of 1) particles having a mean diameter of approximately 0.010 inches (250 microns), and 2) particles having a mean diameter of approximately 0.025 inches (630 microns), both determined by sieving, has been found to work successfully. For the

particular particles used, the diameter range for the smaller particles was between about 0.007 inches (180 microns) and about 0.013 inches (330 microns), and the distribution for the larger particles was between about 0.017 inches (430 microns) and about 0.028 inches (710 microns).

In terms of particle numbers, if comparable packing configurations are assumed for the two sizes, the equal volumes correspond to a smaller particle to larger particle ratio of approximately 16:1. The use of particles of this type in a substantially single layer on a stepped surface has been found to result in a surface roughness substantially greater than that achieved with a single mode distribution of particles having a mean diameter anywhere in the range from about 0.010 inches (250 microns) to about 0.040 inches (1000 microns).

II. SS/NSS Coatings

In accordance with other embodiments of the invention, the surface of the coating is made irregular through the use of both SS and NSS particles (referred to herein as an "SS/NSS coating"). Coatings of this type can be applied to the surface of a prosthesis in single layer or multiple layer configurations.

As with the coatings employing only SS particles, the coatings employing SS and NSS particles can have an at least bimodal distribution and that distribution can be obtained by forming a mixture of at least two sets of sieve-selected particles having different mean diameters. Alternatively, the distribution can be substantially unimodal, although still formed by mixing two sets of sieve-selected particles, with one set being of SS particles and the other of NSS particles.

The SS particles of an SS/NSS coating provide support for the NSS particles. They thus perform a

similar function to that performed by the smaller particles of an at least bimodal SS/SS coating. In conformance with that function, the SS particles of an SS/NSS coating preferably have a mean diameter which is at least somewhat smaller than the mean diameter of the NSS particles. The difference in mean diameters, however, need not be so large as to result in two distinct peaks on a particle size distribution plot, although, if desired, the difference may be so large.

Since the NSS particles inherently provide surface roughness because of their non-spherical shape, the NSS particles of an SS/NSS coating need not be spaced-apart like the larger SS particles of an at least bimodal SS/SS coating. Accordingly, the numbers of SS and NSS particles in an SS/NSS coating need not be as disparate as in an SS/SS coating and in the preferred embodiments of the invention, the numbers of SS and NSS particles are substantially equal in the final coating.

Because SS particles tend to adhere and integrate into the coating more readily than NSS particles during the coating process, such substantially equal numbers of SS and NSS particles can be achieved by beginning with an unequal mixture of particles. For example, to achieve a 50:50 mixture in the final coating, it has been found preferable to apply a 70:30 (NSS:SS) mixture to the surface of the prosthesis which is to be coated. More generally, for any desired NSS:SS ratio in the final coating, a somewhat large ratio is preferably used in the mixture which is applied to the prosthesis to take account of the difference in adherence/integration of NSS particles compared to SS particles.

The NSS particles can be manufactured by various techniques suitable for forming irregular particles. For example, for particles composed of titanium, 6 Al, 4V (ASTM F-136), the desired irregular shape can be

obtained by ball milling the material after it has been hydrogen embrittled, i.e., subjected to a hydride-dehydride process. The particles are then vacuum annealed to reestablish the F136 chemistry. Processing of this type is available from various companies including Powder Alloy Corp (Cincinnati, Ohio).

Figures 8 and 9 are photomicrographs showing an SS/NSS coating having NSS particles prepared in accordance with the foregoing procedure. In particular, the NSS particles had a nominal size range of from 0.0098 inches (250 microns) to 0.0234 inches (600 microns) as defined by -30 +60 mesh sieve analysis. The SS particles used to prepare this coating had a nominal size range from 0.0083 inches (210 microns) to 0.0098 inches (250 microns) as defined by -60 +70 mesh sieve analysis. These SS particles were composed of titanium (ASTM F67).

The two particle types were mixed together in approximately a 70:30 ratio (NSS:SS) by volume and then applied to the sample surface, with a resulting approximately 50:50 particle type mixture on that surface. As shown in Figures 8 and 9, the coating mixture was applied in a single layer, although a multiple layer configuration can be used if desired. The coating was sintered to the substrate material using a heating cycle that gave a 25 MPa minimum shear strength and tensile strength when measured by the ASTM 1044 and 1147 methods.

The roughness of the surface produced through the use of SS and NSS particles is evident from the photomicrographs of Figures 8 and 9.

III. The Bimodal Size Distribution

The differences between the particle distribution for the at least bimodal coatings of the invention (whether of the SS/SS or of the SS/NSS type) and the

particle distributions for prior art coatings is illustrated in Figures 1 through 5.

Figure 1 shows cross-sectional views through typical coatings used in the prior art. More particularly, Figure 1A shows a multi-layer construction 20 using relatively fine particles 22, e.g., particles having a mean diameter of about 0.006 inches (150 microns), Figure 1B shows a multi-layer construction 24 using somewhat larger particles 26, e.g., particles having a mean diameter in the range from about 0.025 inches (630 microns) to about 0.040 inches (1000 microns), and Figure 1C shows a single layer construction on a stepped prosthesis surface 30 using particles 32 having a mean diameter of about 0.010 inches (250 microns).

Representative plots of number of particles (n) versus particle diameter (d) for the constructions of Figures 1A, 1B, and 1C are shown in Figures 2A, 2B, and 2C, respectively. As shown therein, each of the distributions is single-moded, i.e., each distribution has one discernible peak.

Figure 3 shows cross-sectional views through representative coatings constructed in accordance with the invention using two sets of sieve-selected particles having different mean diameters. In particular, Figure 3A shows a single-layer construction 34 on a prosthesis having a smooth outer surface 36, Figure 3B shows a single-layer construction 38 on a prosthesis having a stepped outer surface 40, and Figure 3C shows a multi-layer construction 42 on a prosthesis having a stepped outer surface 44. Figure 4 shows a plan view of the coating 13 for the constructions of Figures 3B and 3C. It should be noted in each of these figures that the distribution of the larger particles 46 within the matrix of the smaller particles 48 is substantially random.

Figure 5 is a plot of number of particles (n) versus particle diameter (d) for the constructions of Figure 3. As shown in this figure, the distribution is bimodal, i.e., there are two discernible peaks in this figure. It should be noted that although the valley between the peaks in this figure drops to zero, in general, the distributions for the two sets can overlap so that the valley need not go all the way to zero. Also, if more than two sets of particle sizes are used, the n versus d plot will have more than two peaks.

It should be noted that for SS/NSS coatings, the single layer, multi-layer, and stepped outer surface embodiments shown in Figures 3 and 4 can be used for particle distributions which are substantially unimodal, i.e., for particle distributions which are not at least bimodal.

IV. Stepped-Surface Prosthesis

As discussed above, the coatings of the invention whether of the SS/SS or the SS/NSS type can be used with prostheses having stepped surfaces. Figure 7 shows a preferred construction for the stepped surface of Figure 3C when used on a spherically-shaped cup of the type shown in Figure 6.

As illustrated in this figure, the cross-sectional shape of each step 50 is oriented similarly relative to a radial line 52 emanating from the center 54 of the sphere 56. This construction allows all of the steps to have a similar shape irrespective of their azimuthal location on the surface of the sphere. It also reinforces the adherence of the coating to the prosthesis when implanted in bone since the forces between the bone and the coating tend to drive the particles into the corners 58 of the steps. Preferably, the steps have azimuthal spacings 60 and radial depths 62 on the

order of 2.5 millimeters or less and 1.0 millimeters or less, respectively.

5 A variety of modifications which do not depart from the scope and spirit of the invention will be evident to persons of ordinary skill in the art from the disclosure herein. The following claims are intended to cover the specific embodiments set forth herein as well as such modifications, variations, and equivalents.

What is claimed is:

1. A prosthesis for implantation in a body having an outer surface at least a portion of which has a sintered coating comprising metallic particles having a size distribution which a) is not unimodal and b) is at least bimodal such that the size distribution includes at least two discernible peaks, one of which corresponds to smaller particles and the other of which to larger particles, wherein the coating comprises less than two complete layers of particles and wherein (i) the smaller particles form a matrix in which the larger particles are distributed, (ii) the larger particles are spaced apart from one another and project above the matrix, and (iii) there are sintered junctions between the larger particles and the smaller particles.

2. The prosthesis of Claim 1 wherein the portion of the outer surface which has the sintered coating is stepped.

3. The prosthesis of Claim 1 wherein the coating comprises substantially a single layer of particles.

4. A prosthesis for implantation in a body having an outer surface at least a portion of which has a sintered coating comprising at least two sets of metallic particles one of the sets having a larger mean diameter and the other of the sets having a smaller mean diameter, said larger and smaller mean diameters having a predetermined ratio, wherein the coating comprises less than two complete layers of particles and wherein (i) the particles having the smaller mean diameter form a matrix in which the particles having the larger mean diameter are distributed, (ii) the particles having the larger mean diameter are spaced apart from one another and project above the matrix, (iii) there are sintered junctions between particles having the larger mean diameter and particles having the smaller mean diameter, and (iv)

the at least two sets of metallic particles have a size distribution which a) is not unimodal and b) is at least bimodal such that the size distribution includes at least two discernible peaks.

5. The prosthesis of Claim 4 wherein the predetermined ratio is between about 2:1 and about 7:1.

6. The prosthesis of Claim 5 wherein the predetermined ratio is about 2.5:1.0.

7. The prosthesis of Claim 6 wherein the mean diameter for the particles having the larger mean diameter is about 630 microns and the mean diameter for the particles having the smaller mean diameter is about 250 microns.

8. The prosthesis of Claim 4 wherein the ratio of the number of particles having the smaller mean diameter to the number of particles having the larger mean diameter is between about 4:1 and about 40:1.

9. The prosthesis of Claim 8 wherein the ratio is about 16:1.

10. The prosthesis of Claim 4 wherein the coating is formed by mixing together equal volumes of the particles having the smaller mean diameter and the particles having the larger mean diameter.

11. A prosthesis for implantation in a body having an outer surface at least a portion of which has a sintered coating, said coating having a maximum thickness and comprising at least two sets of metallic particles, one of the sets having a larger mean diameter and the other of the sets having a smaller mean diameter, wherein the particles having the smaller mean diameter exist on the outer surface in substantially a single layer and the particles having the larger mean diameter define the maximum thickness of the coating and wherein the at least two sets of metallic particles have a size distribution which a) is not unimodal and b) is at least bimodal such that

the size distribution includes at least two discernible peaks.

12. The prosthesis of Claim 11 wherein the coating is formed by mixing together equal volumes of the particles having the smaller mean diameter and the particles having the larger mean diameter.

13. A prosthesis for implantation in a body having an outer surface at least a portion of which has a sintered coating, said coating having a maximum thickness and comprising metallic particles having a size distribution which a) is not unimodal and b) is at least bimodal such that the size distribution includes at least two discernible peaks, one of which corresponds to smaller particles and the other of which to larger particles, wherein the smaller particles exist on the outer surface in substantially a single layer and the larger particles define the maximum thickness of the coating.

14. An acetabular prosthesis comprising a body having a substantially spherical outer surface at least a portion of which is stepped, said steps a) having similar radial cross-sectional shapes irrespective of their azimuthal locations on the surface of the prosthesis, and b) being substantially covered with a sintered coating of particles.

15. The acetabular prosthesis of Claim 14 wherein the azimuthal spacing between the steps is on the order of 2.5 millimeters or less.

16. The acetabular prosthesis of Claim 14 wherein the radial depth of the steps is on the order of 1.0 millimeter or less.

17. The acetabular prosthesis of Claim 14 wherein the sintered coating comprises at least two sets of particles having different mean diameters.

18. A prosthesis for implantation in a body having an outer surface at least a portion of which has a sintered coating comprising at least two sets of

metallic particles one of said at least two sets being composed of spherically-shaped particles and another of said at least two sets being composed of non-spherically-shaped particles.

19. The prosthesis of Claim 18 wherein the portion of the outer surface which has the sintered coating is stepped.

20. The prosthesis of Claim 18 wherein the coating comprises less than two complete layers of particles.

21. The prosthesis of Claim 18 wherein the coating comprises substantially a single layer of particles.

22. The prosthesis of Claim 18 wherein there are sintered junctions between the spherically-shaped particles and the non-spherically-shaped particles.

23. The prosthesis of Claim 18 wherein the at least two sets of metallic particles have a size distribution which a) is not unimodal and b) is at least bimodal such that the size distribution includes at least two discernible peaks.

24. The prosthesis of Claim 18 wherein the set composed of spherically-shaped particles has a smaller mean diameter than the mean diameter of the set composed of non-spherically-shaped particles.

25. The prosthesis of Claim 24 wherein the diameters of the spherically-shaped particles are in the range from about 210 microns to about 250 microns and the diameters of the non-spherically-shaped particles are in the range from about 250 microns to about 600 microns.

26. The prosthesis of Claim 18 wherein the ratio of the number of spherically-shaped particles to the number of non-spherically-shaped particles is between about 1:1 and about 20:1.

27. The prosthesis of Claim 18 wherein the ratio of the number of spherically-shaped particles to the

number of non-spherically-shaped particles is approximately 1:1.

28. The prosthesis of Claim 18 wherein the coating is formed using a mixture of a volume of spherically-shaped particles and a volume of non-spherically-shaped particles, the volume of non-spherically-shaped particles being greater than the volume of spherically-shaped particles.

29. The prosthesis of Claim 28 wherein the ratio of the volume of non-spherically-shaped particles to the volume of spherically-shaped particles is approximately 70:30.

FIG. 1A.

PRIOR ART




FIG. 1B.




FIG. 1C.




FIG. 3A.




FIG. 2A.

PRIOR ART




FIG. 2B.




FIG. 2C.





FIG. 3B.



2/3

FIG. 3C.




FIG. 5.




FIG. 4.




FIG. 6.





FIG. 7.



3/3




FIG. 8



FIG. 9